

FASSON® Offset&Laser MC White FSC

Issue August 2019

Introduction

A premium-quality, machine-coated woodfree paper, semi-gloss, white.

Description

Face : A premium-quality, machine-coated woodfree, white paper with a semi-gloss finish. Front material is FSC® certified (FSC MIX CREDIT CU-COC-807907, Licence Code: FSC-C004451).

Availability

Adhesive ➡ Permanent

Backing U

No cracklines

x

Printing & Conversion

Offset printing.

Laser printing/Dry toner copiers: Suitable for most popular models. Tightly defined release characteristics avoid pre-dispensing during the printing process.

Inkjet printing: Some models of desktop inkjet printers have paper thickness limitations which can cause feed problems.

Before applying the label, the surface must be clean, dry and grease-free.

Note : Please test the self-adhesive construction first to confirm compatibility.

Features : Excellent layflatness, enabling high speed printing
 Excellent guillotining and kiss-diecutting performance.
 Fast drying paper, enabling quick finishing (like cutting, die-cutting etc.)
 High temperature resistant adhesive (up to 180°C) enabling proper paper transport through dry toner copiers/-laser printers.

Recommendations for use

A variety of labels for: barcoding, addressing, inventory, product identification labels and other variably imprinted messages. For indoor use.

General

Shelf life : 2 years stored at 20°C / 55% R.H.

Total caliper (±10%) : 164 micron

For information regarding EHS regulation please visit our website under downloads “Technical bulletins” TB 7.8 Product Compliance Fasson Offset” and for technical guidance “Technical bulletins” – Offset printing.

PRODUCT CHARACTERISTICS

Fasson® Offset&Laser MC White FSC

Physical properties

Face

Basis weight	: 80 g/m ²	ISO 536
Caliper	: 68 micron	ISO 534
Tensile	: 5.2 kN/m MD	ISO 1924/2
Opacity	: 87 %	ISO 2471

Adhesive

Permanent : General-purpose emulsion-based permanent adhesive with a high initial tack and high adhesion on most common substrates

	Permanent
Adhesion (N/m) (FTM 2 on steel/20 min. bond time)	365
Tack (N/m) (FTM 9 on glass)	380
Minimum application temperature	> +5
Service temperature range up to 24 hrs (°C)	+ 80
up to 1 hr (°C)	+ 110
Resistance to cold (°C) ¹⁾ down to	- 40

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs

Backing

No cracklines : A bleached one-side-coated white kraft, especially designed for sheet products, featuring minimal moisture sensitivity

Basis weight	: 78 g/m ²	ISO 536
Caliper	: 82 micron	ISO 534

Warranty: All Avery Dennison and FASSON® brand products statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and FASSON® brand products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison and FASSON® brand products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.

Important: Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty.