

FASSON® Gum Twin FSC

Issue August 2019

Introduction

A self-adhesive construction consisting of a white paper carrier, coated both sides with a supertack adhesive and provided with two release liners.

Description

Carrier: Woodfree offset paper, white. Front material is FSC® certified (FSC MIX CREDIT CU-COC-807907, Licence Code: FSC-C004451).

Availability

<i>Backing</i> ↴	<i>Adhesive</i> ➡	Supertack (both sides)
No cracklines (both sides)		x

Printing & Conversion

Offset printing.

Before applying the label, the surface must be clean, dry and grease-free.

Recommendations for use

To make printed matter self-adhesive, for mounting photographs, showcard assembly, etc.
For indoor use.

General

Shelf life : 2 years stored at 20°C / 55% R.H.
Total caliper (±10%) : 280 micron

For information regarding EHS regulation please visit our website under downloads “Technical bulletins“ TB 7.8 Product Compliance Fasson Offset” and for technical guidance “Technical bulletins“ – Offset printing.

Physical properties

	Top liner	Carrier	Bottom liner		
Basis weight	: 78	68	80	g/m ²	ISO 536
Caliper	: 82	78	82	micron	ISO 534

Adhesive

Supertack : An emulsion-based permanent adhesive specially developed for apolar and rough surfaces. High initial tack combined with strong permanent bond.

	Supertack
Adhesion (N/m) (FTM 2 on steel/20 min. bond time)	460
Tack (N/m) (FTM 9 on glass)	504
Minimum application temperature	> +5
Service temperature range up to 24 hrs (°C)	+ 80
up to 1 hr (°C)	+ 110
Resistance to cold (°C) ¹⁾ down to	- 40

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs

Warranty: All Avery Dennison and FASSON® brand products statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison and FASSON® brand products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison and FASSON® brand products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>.

Important: Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty.